

Model for Predicting the Concentration of Sulphur Removed During Temperature Enhanced Oxidation of Iron Oxide Ore

Chukwuka Ikechukwu Nwoye^{*1}, Stanley Ofoegbu², Uchenna Nwoye³, Stanley Inyama⁴, Hilary Eke¹
Cajetan Nlebedim⁵

1 Department of Materials and Metallurgical Engineering Federal University of Technology, P.M.B 1526
Owerri, Nigeria.

2 Department of Materials Science, Aveiro University Portugal.

3 Data Processing, Modelling and Simulation Unit, Weatherford Nig. Ltd. Port-Harcourt Nigeria.

4 Department of Industrial Mathematics, Federal University of Technology, P.M.B 1526
Owerri, Nigeria

5 Department of Materials Science, University of Cadiff, Wales, United Kingdom.

chikeyn@yahoo.com

Abstract: Model for predicting the concentration of sulphur removed during temperature enhanced oxidation of iron oxide ore has been derived. The model;

$$\%S = \left(\frac{0.1011}{\text{Log}T} \right)$$

was found to predict the concentration of sulphur removed, very close to the corresponding %S values obtained from the actual experimental process. It was found that the model is dependent on the values of the treatment temperature used during the desulphurization process. The validity of the model is believed to be rooted in the expression $[(T)^{\%S}] = \alpha/k_n$ where both sides of the relationship are correspondingly almost equal. The positive or negative deviation of each of the model-predicted values of %S from those of the corresponding experimental values was found to be less than 37% which is quite within the range of acceptable deviation limit of experimental results, hence showing the validity and usefulness of the model for predictive analysis. [Journal of American Science 2009;5(4):49-54]. (ISSN: 1545-1003).

Keywords: Model, Prediction, Sulphur Removed, Oxidation, Temperature, Iron Oxide Ore.

1. Introduction

Agbaja iron ore deposit is the largest known Nigerian iron ore deposit estimated at 1250 metric tonnes of ore reserve. It consists of oolitic and pisolitic structures rich in iron oxides, in a matrix that is predominantly clay. The principal constituent mineral is goethite, with minor hematite, maghemite, siderite, quartz, kaolinite pyrite and an average of 0.09%S (Uwadielle, 1984).

An intensive and selective oil agglomeration of Agbaja iron ore has been carried out (Uwadielle, 1990). The researcher, starting from the crude ore Fe content (45.6%), concentrated the ore by oil agglomeration technique to 90% Fe recovery and 65% Fe assay. He stated that the ore require grinding to minus 5 μ m to effect adequate liberation. These results were obtained at optimum pH 9. Successful studies on the effect of temperature on magnetizing reduction of Agbaja iron ore have been carried out (Uwadielle and Whewell, 1988). The results of the investigation showed that the fine-grained oolitic Agbaja iron ore, which is not responsive to conventional processing techniques, can be upgraded by the magnetizing reduction method with an Fe recovery of 87.3% and Fe assay of 60% at 600^oC.

Attempt has been made to enhance concentrate Fe recovery (Kulkarni and Somasundaran, 1980). The researchers stated that concentrate Fe recovery

decreases progressively below pH 8. In this pH region, oleate used is present as dispersion of oleic acid, and its adsorption on the surface of the iron oxides is similar to the process of hetero-coagulation involving positively charged iron oxide particles and negatively charged oleic acid droplet.

Agbaja oolitic iron ore, which has not been responsive to so many upgrading processes, has been upgraded to 73.4% Fe assay (starting from as-received concentrate assaying 56.2%Fe) by under taking a process referred to as pyrometallurgical-oxidation method (Nwoye, 2008). Main parameters investigated were the effects of treatment temperature and oxidant (KClO₃) on the upgrading process. It was established that 800^oC is the optimum temperature for the upgrading step considering the range of temperature used (500-800^oC). It was observed from results of the investigation that both oxidant and temperature increase (up to 12g per 50g of iron ore and maximum of 800^oC respectively) during the process are vital conditions for improving on the grade of the ore concentrate.

Nwoye et al (2009) derived a model for computational analysis of the concentration of iron upgraded during dry beneficiation of iron oxide ore.

The model;

$$\%Fe = 2.25[(\ln(T/\mu))^{2.58}] \quad (1)$$

shows that the concentration of upgraded iron is dependent on the treatment temperature T , used when the mass of iron oxide ore μ , added is constant.

Nwoye (2008) carried out desulphurization of Agbaja iron oxide ore concentrate using solid potassium trioxochlorate (V) ($KClO_3$) as oxidant. The concentrate was treated at a temperature range 500 – 800°C. The results of the investigation revealed that simultaneous increase in both the percentage of the oxidant added (up to 15g per 50g of ore) and treatment temperature (maximum 800°C) used give the ideal conditions for increased desulphurization efficiency. This translates into high desulphurization efficiency when both oxidant concentration (up to 15g per 50g of ore) and treatment temperature (maximum 800°C) are high.

The mechanism and process analysis of desulphurization of Agbaja iron ore concentrate using powdered potassium trioxochlorate (v) ($KClO_3$) as oxidant has been reported (Nwoye, 2009). Concentrates were treated at a temperature range 500 – 800°C. Results of the process analysis indicate that oxygen required for the desulphurization process was produced following decomposition of $KClO_3$ within a temperature range 375-502°C. It was observed that this temperature range is the Gas Evolution Temperature Range (GETR) for sulphur present in Agbaja iron ore. Sulphur vapour and oxygen gas produced at this temperature range were believed to have reacted to form and liberate SO_2 . The process analysis suggests that the mechanism of the desulphurization process involves gaseous state interaction between oxygen and sulphur through molecular combination. The results for the extent of desulphurization reveal that simultaneous increase in both the percentage of the oxidant added and treatment temperature used (up to 15g $KClO_3$ per 50g of ore and maximum of 800°C respectively) are the ideal conditions for the best desulphurization efficiency.

Investigations made by Bardenheuer and Geller (1934) indicated that the sulphur transfer from metal to slag or slag to gas during desulphurization involves oxygen transfer in the opposite direction. They posited that the mechanism of such desulphurization involves oxidation of sulphur resident in the metal or slag by oxygen from the slag through ionic exchange between the oxygen and sulphur, since the whole system is made up of liquid/molten condition during this process. They maintained that oxygen in the slag comes from CaO , which is one of the products of decomposition of $CaCO_3$ deposited into the slag as a slag forming agent.

St Pierre and Chipman (1956), on studying gas-slag system during iron making discovered that at oxygen partial pressure below about 10^{-5} atm., sulphur dissolves in the melt as sulphide ions; at

oxygen partial pressure higher than 10^{-3} atm., sulphur enters the melt as sulphate ions. In both cases, they stated that both the sulphide and sulphate ions leave the furnace through the slag. They therefore concluded that the mechanism of such desulphurization process is oxidation of sulphur by oxygen from the slag through ionic exchange between the two participating elements.

It was found by Turkdogan and Darken (1961) that at a temperature well below about 1600°C, the pyrosulphate reaction also occurs. They found that this reaction was an enhancement to the desulphurization process actually taking place in the furnace. Also oxygen for this process was found to come from the slag, engaging sulphur in ionic exchange; being the mechanism of such process.

It was discovered that one of the most important factors influencing the desulphurization process during iron making is the state of oxidation of the bath (Pehlke et.al 1975) .

Nwoye et al. (2009) derived a model for the predictive analysis of the concentration of sulphur removed as result of the molecular-oxygen-induced desulphurization of iron oxide ore (potassium chlorate being the oxidant). The model;

$$\%S = \left(\frac{0.0415}{\text{Log } \gamma} \right) \quad (2)$$

was found to predict the concentration of sulphur removed, very close to the corresponding %S values obtained from the actual experimental process. It was found that the model is dependent on the values of the weight-input of the oxidant γ , ($KClO_3$) during the desulphurization process. The validity of the model is believed to be rooted in the expression $k_n[(\gamma)^{\mu\%S}] = T/\alpha$ where both sides of the expression are correspondingly almost equal. The positive or negative deviation of each of the model-predicted values of %S from those of the corresponding experimental values was found to be less than 33% which is quite within the range of acceptable deviation limit of experimental results.

Nwoye et al (2009) derived a model for computational analysis of the concentration of sulphur removed during oxidation of iron oxide ore by powdered potassium chlorate. The model;

$$\%S = \left(\frac{0.0357}{\text{Log } \alpha} \right) \quad (3)$$

indicates that the predicted %S is dependent on the weight-input of $KClO_3$ α , added during the desulphurization process. The maximum deviation of the model-predicted values of %S from those of the corresponding experimental values was found to be less than 37%

Model for predicting the concentration of sulphur removed during gaseous desulphurization of iron oxide ore has been derived by Nwoye et al. (2009). The model;



$$\%S = \left(\frac{0.0745}{\text{Log}T} \right) \quad (4)$$

shows that the predicted %S is dependent on the treatment temperature T, used during the desulphurization process.

The aim of this work is to derive a model for predicting the concentration of sulphur removed during temperature enhanced oxidation of Agbaja (Nigerian) iron oxide ore

2. Model

The solid phase (ore) is assumed to be stationary, contains some unreduced iron remaining in the ore. It was found (Nwoye, 2008) that oxygen gas from the decomposition of KClO₃ attacked the ore in a gas-solid reaction, hence removing (through oxidation) the sulphur present in the ore in the form of SO₂. Equations (5) and (6) show this.



2.1 Model Formulation

Experimental data obtained from research work (Nwoye,2007) carried out at SynchroWell Research Laboratory, Enugu were used for this work. Results of the experiment as presented in report (Nwoye, 2007) and used for the model formulation are as shown in Table 1.

Computational analysis of the experimental data shown in Table 1, gave rise to Table 2 which indicate that;

$$[(T)^{\gamma\%S}] = \alpha/k_n \text{ (approximately)} \quad (7)$$

$$k_n [(T)^{\gamma\%S}] = \alpha \quad (8)$$

Taking logarithm of both sides

$$\text{Log} (k_n[(T)^{\gamma\%S}]) = \text{Log} \alpha \quad (9)$$

$$\text{Log}k_n + \text{Log} [(T)^{\gamma\%S}] = \text{Log} \alpha \quad (10)$$

$$\text{Log}k_n + \gamma \%S \text{Log}T = \text{Log} \alpha \quad (11)$$

$$\gamma \%S \text{Log}T = \text{Log} \alpha - \text{Log} k_n \quad (12)$$

$$\%S = \frac{\text{Log} \alpha - \text{Log} k_n}{\gamma \text{Log}T} \quad (13)$$

Introducing the values of α, k_n and γ into equation (13) (since the are constants) and evaluating further, reduces it to;

$$\%S = \frac{0.1011}{\text{Log}T} \quad (14)$$

Therefore

$$\%S = \frac{D_f}{\text{Log}T} \quad (15)$$

Where

%S = Concentration of sulphur removed during the pyrometallurgical-oxidation process.

k_n = 8.30 (Decomposition coefficient of KClO₃ relative to its weight input (10g per 50g of the iron ore) determined in the experiment (Nwoye,2007)

(γ)= 0.8 (Temperature coefficient relative to weight-input of KClO₃) determined

in the experiment (Nwoye,2007)
 (α) = Weight of KClO₃ added as oxidant (g)
 T = Treatment temperature used for the process (°C)
 D_f=0.1011 (Assumed desulphurization enhancement factor)

Table 1: Variation of concentration of sulphur removed with treatment temperature (Nwoye,2007)

T (°C)	M	%S
500	50	0.030
550	50	0.035
600	50	0.040
650	50	0.043
700	50	0.050
750	50	0.055

Table 2: Variation of α/k_n with T^{γ%S}

α/k _n	T ^{γ%S}
1.2048	1.1608
1.2048	1.1932
1.2048	1.2272
1.2048	1.2496
1.2048	1.2996
1.2048	1.3381

3. Boundary and Initial Condition

Consider iron ore (in a furnace) mixed with potassium chlorate (oxidant). The furnace atmosphere is not contaminated i.e (free of unwanted gases and dusts). Initially, atmospheric levels of oxygen are assumed just before the decomposition of KClO₃ (due to air in the furnace).Weight, M of iron oxide ore used; (50g), and treatment time; 360secs. were used. Treatment temperature range; 500-750°C, ore grain size; 150µm, and weight of KClO₃ (oxidant); 10g were also used. These and other process conditions are as stated in the experimental technique (Nwoye, 2007).

The boundary conditions are: furnace oxygen atmosphere due to decomposition of KClO₃ (since the furnace was air-tight closed) at the top and bottom of the ore particles interacting with the gas phase. At the bottom of the particles, a zero gradient for the gas scalar are assumed and also for the gas phase at the top of the particles. The reduced iron is stationary. The sides of the particles are taken to be symmetries.

4. Model Validation

The formulated model was validated by direct analysis and comparison of %S values predicted by the model and those obtained from the experiment for equality or near equality.

Analysis and comparison between these %S values reveal deviations of model-predicted %S values from those of the experiment. This is attributed to the fact that the surface properties of the ore and the

physiochemical interactions between the ore and the oxidant (under the influence of the treatment temperature) which were found to have played vital roles during the oxidation process (Nwoye, 2007) were not considered during the model formulation. This necessitated the introduction of correction factor, to bring the model-predicted %S values to those of the experimental %S values (Table 3).

Deviation (Dv) (%) of model-predicted %S values from experimental %S values is given by

$$Dv = \left(\frac{Dp - DE}{DE} \right) \times 100 \quad (16)$$

Where Dp = Predicted %S values from model
DE = Experimental %S values

Correction factor (Cf) is the negative of the deviation i.e

$$Cf = -Dv \quad (17)$$

Therefore

$$Cf = - \left(\frac{Dp - DE}{DE} \right) \times 100 \quad (18)$$

Introduction of the corresponding values of Cf from equation (18) into the model gives exactly the corresponding experimental %S values (Nwoye, 2007).

5. Results and Discussion

The derived model is equation (14) or (15). A comparison of the values of %S from the experiment and those from the model shows minimum positive and negative deviations less than 37% which is quite within the acceptable deviation limit of experimental results hence depicting the reliability and validity of the model. This is shown in Table 3.

The validity of the model is believed to be rooted in equation (7) where both sides of the equation are correspondingly almost equal.

Table 2 also agrees with equation (7) following the values α/k_n and $T^{n\%S}$ evaluated from Table 1 as a result of corresponding computational analysis. The value 0.1011 has a direct relationship with the value of %S as shown in equation (14). This indicates that the constant contributes directly (as a multiplying factor) to the predicted concentration of sulphur removed from the ore. Based on the foregoing, the constant is denoted as desulphurization enhancement factor D_f

Table 3: Comparison between %S removed as predicted by model and as obtained from experiment. (Nwoye, 2007)

%S _{exp}	%S _M	Dv (%)	Cf (%)
0.030	0.0375	+25.00	-25.00
0.035	0.0369	+5.43	-5.43
0.040	0.0364	-9.00	+9.00
0.043	0.0360	-16.28	+16.28
0.050	0.0355	-29.00	+29.00
0.055	0.0352	-36.00	+36.00

Where

%S_{exp} = %S values from experiment
(Nwoye, 2007)

%S_M = %S values predicted by model

6. Conclusion

The model predicts the concentration of sulphur removed during temperature enhanced oxidation of Agbaja iron oxide ore. The validity of the model is believed to be rooted in equation (7) where both sides of the equation are correspondingly almost equal. The deviation of the model-predicted %S values from those of the experiment is less than 37% which is quite within the acceptable deviation limit of experimental results.

Further works should incorporate more process parameters into the model with the aim of reducing the deviations of the model-predicted %S values from those of the experiment

Acknowledgement

The authors thank Dr. Ekeme Udoh, a modelling expert at Linkwell Modelling Centre Calabar for his technical inputs. The management of SynchroWell Nig. Ltd. Enugu is also appreciated for permitting and providing the experimental data used in this work.

Correspondence to:

Chukwuka Ikechukwu Nwoye

Department of Materials and Metallurgical Engineering, Federal University of Technology, P.M.B 1526 Owerri. Imo State, Nigeria.

Cellular phone: 0803 800 6092

Email: chikeyn@yahoo.com

References

- [1]Uwadielle GGOO. Beneficiation Studies of Agbaja Iron Ore. Ph.D Thesis, University of Strathdyde 1984.
- [2]Uwadielle GGOO. Selective Oil Agglomeration of Agbaja Iron Ore. Metallurgical Transaction B 1990: 20a: 23.
- [3]Uwadielle GGOO, Whewell RJ. (1988) Effect of Temperature on magnetizing Reduction of Agbaja Iron ore; Metallurgical Transaction B 1988: 19b: 3.
- [4]Kulkarni KE, Somasundaran DU. Effect of pH on the Concentrate Iron Recovery Using Oleate Solution, Metallurgical Transaction B 1980: 18b:30.
- [5]Nwoye CI. Upgrading of Agbaja Iron Oxide Ore Concentrate by Pyrox Method. JMME 2008: 3(1): 14-16.
- [6]Nwoye CI, Mbuka IE, Menkiti M, Nwoye CC, Nnuka E, Onyemaobi OO. Model for Computational Analysis of the Concentration of Iron Upgraded during Dry Beneficiation of Iron Oxide Ore, Journal of Advances in Science and Technology (in press)

- [7]Nwoye CI. Gaseous Desulphurization of Agbaja Iron Ore Concentrate. Journal of Engineering and Applied Sciences 2008;3(1,2): 72-75.
- [8]Nwoye CI. Process Analysis and Mechanism of Desulphurization of Agbaja Iron Oxide Ore. JMME 2009: 8: 27-32.
- [9]Bardenheuer P, Geller, W. Kais. Wilh. Inst., Eisenforsch 1934: 16:77- 91.
- [10]St.Pierre GR, Chipman J. Trans. AIME 1956: 206:1474-83.
- [11]Turkdogan ET, Darken LS. Trans. Met. Soc. AIME 1961: 221:464-74.
- [12]Pehlke RD, Porter WF, Urban RF, Gaines JM. BOF, Steel Making, Iron &Steel Soc. AIME 1975: 2:142- 153.
- [13] Nwoye CI, Anyakwo CN, Nwoye CU, Inyama S, Ejimofor R, Nwakwuo CC. Model for Predictive Analysis of the Concentration of Sulphur Removed by Molecular-Oxygen-Induced Desulphurization of Iron Oxide Ore, Journal of Nature and Science 2009: 7(3):36-40.
- [14]Nwoye CI, Lee SO, Nwoye CU, Obi MC, Onuoha E, Trans T. Model for Computational Analysis of the Concentration of Sulphur Removed during Oxidation of Iron Oxide Ore by Powdered Potassium Chlorate, Journal of Advances in Science and Technology 2009: 3(1):45-49.
- [15] Nwoye CI, Nwakwuo CC, Nwoye CU, Onugha E, Obiji S, Mbuka IE, Obasi GC. Model for Predicting the Concentration of Sulphur Removed during Gaseous State Desulphurization of Iron Oxide Ore, Journal of Engineering and Earth Sciences (in press)
- [16]Nwoye CI. SynchroWell Research Work Report, DFM Unit, No 2007146, 2007: 35-45.

The Journal of American Science

Normal paper structure for the Journal of American Science:

Each manuscript is suggested to include the following components but authors can do their own ways:

- (1) The complete article title.
- (2) Each author's full name; institution(s) with which each author is affiliated, with city, state/province, zip code, and country; and the name, complete mailing address, telephone number, facsimile number (if available), and email address for all correspondence.
- (3) **You must put at least one email address under the authors' address.**
- (4) Abstract: including Background, Materials and Methods, Results, and Discussions, 100-300 words preferred.
- (5) Key Words.
- (6) Introduction.
- (7) Materials and Methods.
- (8) Results.
- (9) Discussions.
- (10) Acknowledgments.
- (11) Correspondence to.
- (12) References.

Description of Manuscript Preparation and Format:

- (1) Software: Microsoft Word file.
- (2) Font: Normal, Times New Roman, 10 pt, single space.
- (3) Indent: 8 spaces in the beginning of each new paragraph.
- (4) Manuscript: Don't use "Footnote" or "Header and Footer".
- (5) Spelling check: Do spelling check when you finish.
- (6) Color: Email and website addresses are blue, and all other contents are black.
- (7) Abstract: 100-300 words are preferred, and remember to add "[The Journal of American Science. 2009;x(x):xx-xx]. (ISSN 1545-1003)" in the end of abstract.
- (8) Page setup: Margins: top 72 pt, bottom 72 pt, left 72 pt, right 72 pt.
- (9) Paper size: Letter, width 612 pt, height 792 pt.
- (10) Layout: Header 36 pt, Foot 36 pt.
- (11) Title: Use Title Case in the title and subtitles, e.g. "Debt and Agency Costs".
- (12) Figures and Tables: Use full word of figure and table, e.g. "Figure 1. Annual Income of Different Groups", Table 1. Annual Increase of Investment".
- (13) References: Cite 10-20 references preferred, by "last name, year", e.g. "(Smith, 2003)". References should include all the authors' last names and initials, title, journal, year, volume, issue, and pages etc.
- (14) *Reference Examples*: Journal Article: Hacker J, Hentschel U, Dobrindt U. Prokaryotic chromosomes and disease. *Science* 2003;301(34):790-3.
- (15) Book: Berkowitz BA, Katzung BG. Basic and clinical evaluation of new drugs. In: Katzung BG, ed. Basic and clinical pharmacology. Appleton & Lance Publisher. Norwalk, Connecticut, USA. 1995:60-9.
- (16) Insert page number by bottom / center.
- (17) Header for odd: Marsland Press Journal of American Science 2009;x(x):xx-xx.
- (18) Header for even: short title Family name of the first author, et al.
- (19) Footer: <http://www.americanscience.org> americansciencej@gmail.com.
- (20) Submission Address: sciencepub@gmail.com, editor@sciencepub.net, Marsland Press, P.O. Box 21126, Lansing, Michigan 48909, The United States, 347-321-7172.

6/2/2009